


Elevation 1:10



Z11: Purpose made metalwork

To be read with Preliminaries/ General conditions.

310 METAL PRODUCTS

510 PREPARATION FOR APPLICATION OF COATINGS Standards: Generally, as specified in the following clauses.
 Fasteners: Generally, same metal as component, with matching coating and finish.

General: Complete fabrication, and drill fixing holes before applying coatings.

Paint, grease, flux, rust, burrs and sharp arrises: Remove.

515 FABRICATION GENERALLY

Contact between dissimilar metals in components: Avoid

Finished components: Rigid and free from distortion, cracks, burrs and sharp arrises.

 Corner junctions of identical sections: Mitre Moving parts: Free moving without binding.

 Prefinished metals: Do not damage or alter appearance of finish 535 WELDING AND BRAZING GENERALLY Surfaces to be joined: Clean thoroughly

 Joints: Fully bond parent and filler metal throughout with no inclusions, holes, porosity or Tack welds: Use only for temporary attachment

Surfaces of materials that will be self-finished and visible in completed work: Protect from

LLOYD EVANS PRICHARD Boardwalk, 21 Little Peter Street, Manchester, M15 4PS Tel: 0161 834 6251

Flux residue, slag and weld spatter. Remove.

Client Frodsham Borough Council Building / Shouture Proposed Plaque to Entrance Raillings Denving No. 03 As Shown @ A4 Contract No. 100 100 100 100 100 100 100 1	Contract Frodeham War Memorial
--	--------------------------------